

#4/A
6/4/02
Dygs**Door Module****Field of the Invention**

The invention relates to a door module, a compression moulding set for manufacturing a door module, and a process of manufacturing a door module.

Background of the Invention

Door modules are commonly used to cover large cut-out recesses in the inside door panel of a vehicle door. The door module covers such recess in a sealed manner so that a door body is divided into a wet cell lying between a door outside panel, and a dry cell lying between the door module and an adjoining door inside trim. Electrical and electronic components can be prefitted on the door module. Their electrical plug connectors are located solely on the dry cell side.

Known door modules usually consist of a steel carrier to which a separate foam seal is applied in order to provide a sealed coverage of a cut-out recess in an inside door panel. However, several manufacturing steps are usually required to fix the separate foam seal on the steel carrier. The manufacturing process thereby becomes lengthy and costly.

Also known are door modules having injection moulded carriers with integrated seals and other integrated features. However, the integration of seals and other features is limited as is the elasticity of the integrated features due to the structural requirements for the carrier. Moreover, the door modules are produced from a short glass fiber plastic compound; short glass fiber material, however, is expensive.

It is thus desirable to address these disadvantages.

Summary of the Invention

According to one aspect of the invention, a door module for covering a surface cut-out recess in the inside panel of a vehicle door is provided, the door module comprising a substantially rigid structural portion of long glass fiber reinforced plastic, and a substantially

11/14/01
DATE

SIGNATURE

elastic functional portion of plastic substantially free of long glass fibers and formed integrally with the substantially rigid portion. Accordingly, there is provided a door module which achieves integration of rigid structural features (e.g. the carrier) and elastic functional features. Through employing long glass fiber reinforced plastic, the cost of the door module is reduced.

AC 12
The substantially elastic portion may comprise a first lip seal extending along the outer rim area of the door module, for sealing a connection between the door module and the inside panel of the vehicle door. A second lip seal extending parallel to the first lip seal may be provided for extra sealing.

In one embodiment of the invention, the vehicle door body is divided into a wet cell lying between a door outside panel and the door module, and a dry cell lying between the door module and an adjoining door inside trim, and the substantially elastic portion comprises a drip ledge extending into the wet cell along a lower area of the door module when installed in the vehicle door, for repelling water from a connection between the door module and the inside panel of the vehicle door.

In another embodiment of the invention, the vehicle door body is also divided into a wet cell lying between a door outside panel and the door module, and a dry cell lying between the door module and an adjoining door inside trim, and the substantially elastic portion comprises one or more clips extending in the dry cell, for attachment of a wire harness, electrical connectors and suchlike. In addition, the substantially elastic portion may comprise attachment elements for attaching the door inside trim, electrical and/or electronic elements to the door module within the dry cell. Furthermore, the substantially elastic portion may comprise attachment means for attaching noise reduction elements to the door module within the dry cell and/or the wet cell. This achieves a high degree of flexibility in terms of providing integrated functional features as required for any given type of door and special equipment associated with the vehicle door.

In one embodiment of the invention, the substantially elastic portion comprises a lip for contacting a door window when retracted into the wet cell of the vehicle door, thereby reducing

movements of the door window perpendicular to the window plane. This creates an „anti-rattle“ device.

Preferably, the long glass fibers of the long glass fiber enforced plastic material are staple glass fibers, i.e. long glass fibers of limited length. Preferably, the long glass fibers have a length of approximately 20 mm, and a thickness of approximately 0.02 mm. The glass fiber portion of the long glass fiber enforced plastic material may be between 30 and 70%, and preferably around 40%. The plastic material may be polypropylene.

According to another aspect of the invention, a mould for manufacturing a door module for a vehicle door by compression moulding is provided. The mould is arranged to receive a long glass fiber enriched plastic material, and for shaping a substantially rigid portion of the door module during compression moulding, and comprising one or more cavities of such dimensions that during compression moulding, plastic material substantially free of long glass fibers is forced into at least part of the one or more cavities, shaping a substantially elastic portion of the door module. Such extraction of plastic from the long glass fiber enriched plastic material in the cavities has been established in experiments to be controllable through the specification of cavity dimensions. Accordingly, a mould which allows the provision of substantially rigid features and integrated elastic features can be accomplished in one manufacturing step. The manufacture of door modules is thereby simplified considerably.

Preferably, the mould also comprises a heater for heating the long glass fiber enriched plastic material received in the mould. Thereby, the formability of the long glass fiber enriched plastic material received in the mould is enhanced.

In one embodiment of the invention, the functional structure comprises one or more elastic functional elements such as a lip seal, and the cavity has the inverse shape of the one or more elastic functional elements to be formed during compression moulding. Thus, by providing suitable cavities, elastic functional elements of any desired shape (and thus function) may be formed.

7
Acont

According to another aspect of the invention, a process of manufacturing a door module for a vehicle door is provided. The process comprises: providing a mould for shaping a substantially rigid portion of the door module, the mould comprising one or more cavities; filling the mould with a long glass fiber enriched plastic material; exerting pressure on the long glass fiber enriched plastic material received in the mould, wherein the one or more cavities in the mould are of such dimensions that plastic material substantially free of long glass fibers is forced into at least part of the one or more cavities; and hardening of the substantially rigid and substantially elastic portions. Accordingly, a simplified manufacturing process is provided which allows the production of door modules having both substantially rigid features as well as integrated elastic functional features. A complicated addition of separate functional features after provision of a carrier is no longer necessary.

Preferably, the long glass fiber enriched plastic material received in the mould is heated before exerting pressure, in order to improve its compressability.

The process may further comprise the step of trimming the functional structure so as to obtain one or more wiring harness clips or any other functional feature required. Through trimming, it is thus possible to realise more sophisticated shapes than by specifying the inverse shape of the required feature in the form of the cavity.

In one embodiment of the invention, the cavity has the inverse shape of a lip extending along the outer rim area of the door module, wherein the lip is bent relative to the surface of the substantially rigid portion so that a cross section of the lip is at an angle to the surface of the substantially rigid portion. Alternatively, this can be achieved by trimming the functional structure so as to obtain a lip whose cross section lip is at an angle to the surface of the substantially rigid portion.

Brief Description of the Drawings

Exemplary embodiments of the invention will now be described by reference to the accompanying drawings, of which:

Figure 1 illustrates schematically a vehicle door, in accordance with an embodiment of the invention;

Figure 2a illustrates a cross-sectional view along line A-A in Figure 1 of the door module and the door inside panel shown before assembly;

Figure 2b illustrates a cross-sectional view along line A-A in Figure 1 of the door module and the door inside panel shown after assembly;

Figures 3 illustrates the cross section along line A-A in Figure 1 of an alternative embodiment before assembly;

Figure 4 illustrates the cross section along line A-A in Figure 1 of an alternative embodiment of the invention after assembly;

Figure 5 illustrates a cross-sectional view of part of a door module in accordance with another embodiment of the invention;

Figure 6 illustrates schematically the steps of a process of compression moulding a door module in accordance with an embodiment of the invention;

Figure 7 illustrates a moulding set for compression moulding a door module in a process according to Figure 6;

Figure 8a illustrates a stamp forming part of the moulding set of Figure 7 in the compression step;

Figure 8b illustrates a lip in the bending step;

Figure 9 illustrates a door module in accordance with an embodiment of the invention before trim;

Figure 10 illustrates the door module of Figure 9 after trim;

Figure 11a illustrates a cross-sectional view of the door module in accordance with another embodiment of the invention before trim;

Figure 11b illustrates a top view of the door module in Figure 11a;

Figure 12a illustrates a cross-sectional view of the door module of Figure 11a after trim; and

Figure 12 illustrates a top view of the door module of Figure 11b after trim.

Detailed Description of the Drawings

Figure 1 shows schematically a vehicle door 1 as seen from the outside of a vehicle. For the sake of illustration, the door outside panel of the vehicle door 1 is not shown so that a door inside panel 2 can be seen. The door inside panel 2 is provided with a large surface cut-out recess 3. The recess 3 is covered from the inside by a door module 4 in a sealed manner so that the door body is divided into a wet cell lying between the door outside panel and the door module 4, and a dry cell lying between the door module 4 and an adjoining door inside trim (not shown). The dry cell provides a space for containing electrical and/or electronic components such as an electric motor for driving a window lifter, a control unit for the electric motor, a wiring harness, etc. These components are attached to the door module 4 by clips and other attachment elements, as will be illustrated hereinbelow. Likewise, the door inside trim is attached to the door module by means of clips or otherwise. Since the equipment of a vehicle depends on its specification, the number of components in the dry cell can vary considerably, and as a consequence, so does the requirement for suitable attachment means therefor.

The door module 3 is attached to the door inside panel 2 through attachment means 5. As illustrated in Figure 1 by a first grey zone 6, a contact seal zone is formed around the recess 3 where the door inside panel 2 and the door module 4 are in contact, as is also illustrated in Figure 2. In addition, a lip seal zone 7 is formed by a lip 8 (Figure 2) surrounding the recess 3

and arranged on the door module 4 so as to extend between the door module 4 and the inside door panel 2 (as will also be explained with reference to Figure 2). Furthermore, a drip ledge 9 is provided at the door module 4 in order to provide a drip seal zone. The drip ledge 8 is provided just above the lower contact area of the door module 4 and the inside door panel 2 in order to prevent water from dripping thereon.

Figures 2a and 2b illustrate a cross-sectional view along line A-A in Figure 1. In Figure 2a, the door module 4 and the inside door panel 2 are shown before assembly. Figure 2b illustrates the door module 4 and the inside door panel 2 after assembly. In the orientation of Figures 2a and 2b, the dry cell mentioned in connection of Figure 1 would be on the left of the door module 4, whereas the wet cell would be on the right.

The lip 8 forming the lip seal zone 7 is bent towards the adjacent free end portion 10 of the door module 4. The free end portion 10 is offset laterally relative to the remainder of the door module 4. Thus, when the free end 10 of the door module 4 is fixed to the inside door panel 2, a gap 11 is formed inbetween the door module 4 and the inside door panel 2. The lip 8 is arranged at the door module 4 such as to extend into the gap 11. Since the gap 11 is smaller than the length by which the lip 8 projects perpendicularly from the door module 4, the lip 8 is always in contact with the inside door panel 2 when the door module 4 is attached thereto, thereby forming the lip seal zone 7.

The drip ledge 9 is formed by a lip which is substantially at a right angle to the door module 4 and which is arranged inside the recess 3 adjacent to the lower part of the rim 12 of the inside door panel 2 defining the recess 3. The drip ledge 9 has a perpendicular extension from the door module which is larger than the gap 11. Thus, in the orientation of Figures 2a and 2b, water entering the wet cell from above is prevented from dripping onto the area where the free ends of the door module 4 and the inside door panel 2 adjoin.

Figures 2a and 2b also illustrate the contact seal zone 6 which is formed where the free end 10 of the door module 4 is held in contact with the inside door panel 2 through the attachment means 5 (in the form of a screw connection in Figures 2a and 2b).

Figures 3 and 4 illustrate the cross section along line A-A in Figure 1 of an alternative embodiment before and after assembly, respectively. In this embodiment, two lips 8 are arranged adjacent to one another. The lips 8 extend in parallel to each other around the rim 12 of the inside door panel 2, in order to provide the lip seal zone 6. In contrast to the first embodiment, the gap 11 of this embodiment is provided by means of a flange 13 inbetween the door module 4 and the inside door panel 2, instead of a lateral offset of the end portion 10. As in the first embodiment, the gap 11 is smaller than the length by which the lips 8 project from the door module 4 so that they contact the inside door panel 2 when assembled. Also, the lips 8 are bent towards the end portion 10 so that their free ends point in that direction, before as well as after assembly.

Figure 5 illustrates a cross-sectional view of yet another embodiment of the invention. In this embodiment, the door module 4 comprises a lip 14 for contacting a door window 15 when retracted (partly or fully) into the vehicle door 1. Thereby, undesired movement of the window 15 perpendicular to the window plane is restricted. As a consequence, rattling of the window 15 when retracted is eliminated or at least reduced. The lip 14 at rest (i.e. with the window unretracted) can extend perpendicularly from the door module 4 so that it is only bent into the position shown in Figure 5 by retraction of the window 15. Alternatively, the lip 14 can be pre-bent by a suitable angle relative to the surface of the door module 4 so that the lip tip points away from the bottom end of the window 15 when unretracted. In any case, the lip 14 projects from the door module surface far enough to ensure contact with the window 15.

Figure 6 illustrates schematically a compression moulding process of a door module in accordance with an embodiment of the invention. In a first step S1, a mould is filled with a long glass fiber enriched polypropylene. In a second step S2, the long glass fiber enriched polypropylene is heated in order to assist the moulding process. Subsequently, in a step S3, pressure is exerted to the heated (and thus flexible) long glass fiber enriched polypropylene in the mould. In the mould surface, one or more cavities are provided which have the inverse shape of functional features to be formed as part of the door module (as will be explained in more detail hereinbelow), such as for example the lip 8 or the drip ledge 9. During the step of

pressure exertion, material is forced into the cavity so as to form the functional features, as is explained in more detail hereinbelow. In subsequent steps S4 and S5, the moulded material is hardened and extracted from the mould. Then, a trimming step S6 is applied, in which the functional features are cut to a desired shape, if necessary. Alternatively, trimming actions such as bending can be performed before the hardening step is completed, that is when the moulded material is still flexible and can thus still be formed.

7
Avent
Figure 7 illustrates a mould 16 for compression moulding the door module 4 in a process according to Figure 6. The mould 16 is shown as having a base portion 17 and a separate stamp portion 18 for exerting pressure on material received in the base portion 17. The mould may also be formed in a single piece. The base portion 17 comprises a heater 19 for heating a material 20 received in the base portion 17 in order to facilitate the moulding process. During the moulding process, pressure is exerted onto the material 20 by applying the stamp portion 18, as schematically indicated by force F. Thereby, the material 20 is moulded in accordance with the shape of the mould 17 and the stamp 18. Subsequently, the material 20 is hardened and extracted from the mould 17.

As shown in Figure 8a, a cavity 21 is provided in an inner surface of the mould 16. During compression moulding, the material 19 is forced into the cavity 21 and adopts the inverse shape thereof, whereby a lip 22 is formed. In Figure 8b, the lip 22 is bent while the material 19 has not yet completely hardened.

According to an embodiment of the invention, the material 19 consists of long glass fiber enriched polypropylene. The cavity 21 is shaped and dimensioned such that during compression moulding, the long glass fibers are extracted from the polypropylene at the entry of the cavity 21 such that polypropylene which is substantially free of glass fibers enters the cavity 21. As a consequence, the lip 22 consists of a material different from the remainder of the door module 4. That is, the lip 22 consists of polypropylene which is virtually fiberglass-free, whereas the remainder of the door module 4 consists of fiberglass-reinforced polypropylene. As a further consequence, the lip 22 is substantially elastic, while the main body of the door module 4 is substantially rigid. It is thus possible to produce substantially rigid features (such as the

door module main body) in the same manufacturing step as substantially elastic features (such as the lip 22).

7
A 6/12

Figures 9 and 10 illustrate an embodiment of the invention, in which a lip 23 is formed during the trimming step S6 of Figure 6 by cutting. Figure 9 shows the door module 4 after compression moulding and after the hardening step. The door module comprises a projection 24 having the cross-sectional shape of a fin. By cutting away some of the projection 24, the lip 23 as depicted in Figure 10 is obtained. The lip 23 of Figure 10 can function as a seal (as explained in connection with Figure 2 in respect of the lip 8) or as an "anti-rattle device" (as explained in connection with the lip 14 of Figure 5).

Figures 11a-12b illustrate the manufacture of a wire harness holder 25, each showing a cross sectional view and a top view of part of the door module 4. Figures 11a and 11b show the door module 4 after the hardening step S4 but before the trimming step S6. The door module 4 comprises two fiberglass-enforced projections 26, between which a polypropylene area substantially free of fiberglass is provided. During the trim operation the polypropylene area is cut so as to obtain the wire harness holder 25 as best seen in Figure 12a. Due to the elasticity of the wire harness holder 25, a wire harness can be easily inserted therein and thereby attached to the door module 4.

It is to be noted that the invention is not limited to the embodiments described above. It is envisaged that various modifications and variations to the above described embodiments can be made without falling outside the scope of the present invention as determined from the claims.
